

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

THIS PAGE
IS BLANK (USPTO)



(11) Publication number : **0 554 046 A1**

(12)

EUROPEAN PATENT APPLICATION

(21) Application number : **93300546.4**

(51) Int. Cl.⁵ : **C04B 24/02, C04B 22/08,
C04B 40/00**

(22) Date of filing : **26.01.93**

(30) Priority : **28.01.92 US 827196**

(43) Date of publication of application :
04.08.93 Bulletin 93/31

(84) Designated Contracting States :
**AT BE CH DE DK ES FR GB GR IE IT LI LU NL
PT SE**

(71) Applicant : **W.R. Grace & Co.-Conn.**
Grace Plaza, 1114 Avenue of the Americas
New York, New York 10036-7794 (US)

(72) Inventor : **Arfaei, Ahmad**
72 Stonegate Road
Chelmsford, MA 01824 (US)
Inventor : **Berke, Neal S.**
39 Charlemont Court
Chelmsford, MA 01863 (US)
Inventor : **Jeknavorian, Ara A.**
4 Percheron Road
Chelmsford, MA 01824 (US)

(74) Representative : **Bentham, Stephen**
J.A. Kemp & Co. 14 South Square Gray's Inn
London, WC1R 5LX (GB)

(54) **Hydraulic cement set-accelerating admixtures incorporating glycols.**

(57) New set-accelerating admixtures for hydraulic cement compositions are disclosed. These admixtures incorporate known set accelerators and certain low molecular weight glycols, e.g., glycerol and ethylene glycol, are found to be surprisingly effective in decreasing the initial set time of hydraulic cements, mortars, and concretes, and are advantageous as reduced-temperature set-accelerators.

This invention relates to improvements in set-accelerating admixtures for hydraulic cement compositions such as mortars, grouts and concretes. More particularly the invention relates to novel set-accelerating admixtures and methods for set-acceleration employing the addition of certain low molecular weight glycols, e.g., glycerol and ethylene glycol.

5 Set accelerators are used when it is necessary to work with hydraulic cement compositions at freezing or near-freezing temperatures. The rate of hydration of Portland cement, for example, is very dependent on temperature, such that, at lower temperatures, portland cement compositions will often harden at a rate slower than desired unless the hardening process is accelerated. In addition to accelerating the set, it is desirable to also attain an increase in the rate of early strength development at normal or low temperatures. This reduces
10 curing and protection periods necessary to achieve specified strengths in concrete. Some techniques for accelerating the set are: increasing the proportion of cement in the mix, heating the mix, and using chemical admixtures that act on the components of the mix to increase the rate at which the cement paste sets.

Several chemical set accelerators are well-known. They include alkali hydroxides, silicates, fluorosilicates, calcium formate, sodium chloride, calcium chloride, and calcium nitrate and calcium nitrite.

15 Calcium chloride is widely used because it is easy and inexpensive to produce and its effects on hydraulic cement are predictable and well-documented. However, like sodium chloride, it has the disadvantage of corroding steel. Thus, it can cause the corrosion of steel reinforcing bars in concrete. Other drawbacks of calcium chloride use include reduced compressive strength at later ages, reduced response to air entrainment, and blotching of hardened concrete surfaces (Concrete Admixtures, Dodson: Van Nostrand Reinhold, 1990).

20 It is thus an object of this invention to provide new set-accelerating admixtures which reduce the set time of hydraulic cement compositions at lower temperatures, without inducing or promoting corrosion of steel reinforcement. Further objects of the invention are to provide methods for preparing such cement compositions and to provide methods for reducing the set time of hydraulic cement compositions.

This invention is directed toward new hydraulic cement set-accelerating admixture compositions, to cement
25 compositions containing such admixtures, and to methods for preparing said cement compositions. The admixture compositions comprise a set accelerator component and a C₂ to C₆ glycol component present in an amount effective to increase the set acceleration properties of the set-accelerator component. The invention further relates to a method of making a hydraulic cement composition comprising adding to a cement composition comprising a hydraulic cement binder, a set-accelerating component, and a C₂ to C₆ glycol component
30 in an amount effective to increase the set-acceleration properties of the set-accelerator component, and to a cement composition comprising a hydraulic cement binder, a set-accelerating component, and a C₂ to C₆ glycol component present in an amount effective to increase the set acceleration properties of the set-accelerator component.

It has been found that admixtures comprising a set-accelerating compound and certain low molecular weight glycols are surprisingly effective in reducing the set time of hydraulic cement compositions. Such admixtures are also found to be quite effective at lower working temperatures, i.e., below about 50°F. It appears that these low molecular weight glycols increase the set-acceleration properties of a set-accelerating compound. Additionally, admixtures of this invention may be formulated in such a way as to produce a composition that will inhibit corrosion in steel reinforcing bars commonly imbedded in cement compositions.

40 The term "glycol" as used herein is intended to mean two to six carbon, i.e., "C₂ to C₆", aliphatic di- and trihydric alcohols. Glycols suitable for use in the invention are those such as ethylene glycol, propylene glycol, and glycerol. Other compounds meeting the above definition will be apparent to those skilled in the art. Until now these compounds have not been known to have any set-accelerating qualities, i.e., they have been used primarily as grinding aids and set retarders. For this reason these compounds were not seen as having any
45 value as part of a set-accelerating admixture. As such it was surprising to the inventors that a glycol as described herein could be used with a set-accelerating compound to significantly increase the set acceleration of a cement composition over that obtained by the addition of the set accelerator alone to the cement composition. Thus this invention utilizes the glycol component to give the set acceleration of the cement composition containing the set accelerator a desired "boost."

50 The term "cement composition" as used herein refers to pastes, mortars and concrete compositions comprising a hydraulic cement binder. The above terms are terms of art. Pastes are mixtures composed of a hydraulic cement binder, for example, portland cement, either alone or in combination with fly ash, silica fume or blast furnace slag, and water; mortars are pastes additionally including fine aggregate, and concretes are mortars additionally including coarse aggregate. Such compositions may additionally include other admixtures
55 such as defoaming agents, air-entraining or detraining agents, set retarders, water reducing agents, superplasticizers, and other components known to those in the art for altering properties of the composition. The cement compositions of this invention are formed by mixing required amounts of certain materials, e.g., a hydraulic cement, water, and fine or coarse aggregate, as may be applicable for the particular cement composition being

formed.

The set-accelerating component may be any compound which, when added to a cement composition (as described above), reduces the amount of time required for the cement composition to harden. For example, an alkali or alkaline earth metal salt which is a salt of an organic or inorganic acid may be employed. Although the following list is not meant to be limiting, examples of these compounds are alkali or alkaline earth metal nitrate, nitrite, and formate; alkali or alkaline earth metal salts of Group VI halogen and pseudohalogen acids, such as alkali or alkaline earth metal chloride, bromide, iodide, thiocyanate, thiosulfate and perchlorate; and alkali or alkaline earth metal aluminates, silicates, and hydroxides, e.g., sodium hydroxide. Calcium salts are particularly advantageous, especially calcium nitrate, calcium chloride, and calcium formate, and calcium nitrite.

It is also feasible to use a mixture of alkali or alkaline earth metal salts, for example, a mixture of calcium nitrate and calcium nitrite. Any ratio of the salts used may be employed; in a preferred calcium nitrate/calcium nitrite mixture, a range of weight ratios of from about 1:3 to 3:1 may be used. The inventors have found that such an admixture, using a calcium nitrate/calcium nitrite mixture as the set-accelerator component, is beneficial in inhibiting corrosion in steel reinforcing bars commonly imbedded in cement compositions.

If the set-accelerating component and glycol component are added to the cement composition separately, the glycol may be added, generally, in percent solids on solids ("% s/s"), in the range of about 0.05% s/s to 1.0% s/s (based on the weight of hydraulic cement binder in the cement composition), with a preferred range of about 0.1% s/s to 0.75% s/s, such concentrations being generally those which provide the desired boost in acceleration. The set-accelerating component may be added in the usual amounts necessary for set-acceleration, but generally in a range of from about 0.05% s/s to about 4.0% s/s. (Note that through the use of a glycol component of the invention, it is also possible to reduce the amount of set-accelerator component normally required for a certain level of set acceleration, because of the better set-acceleration provided by the combination of the glycol and the set-accelerator.)

However, the inventors find it is preferable to combine the glycol component and the set-accelerating component in desired amounts before addition to a cement composition, so only one composition need be metered out and added to the cement composition. This is a simpler and more precise method than adding each component separately and reduces the opportunity for error in dispensing the correct formulation. If the set-accelerating component and glycol component are to be mixed before addition to a cement composition, the glycol component and the set-accelerating component may be combined in any proportion effective to give the desired results. Generally, the amount of the glycol in the mixture may range from about 0.5 to 40 weight % (based on the combined weight of glycol component and accelerator component), and preferably from about 2 to 30 weight %.

An admixture of the invention should be mixed into a hydraulic cement composition in an amount effective to allow the acceleration desired. The specific amount of the admixture can be readily determined and will depend on the cement composition, the ratio of components of the composition, and the degree of acceleration desired. The admixture is generally added to a cement composition in an amount which, as noted above, provides a glycol concentration of from about 0.05% s/s to 1.0% s/s, preferably from about 0.1% s/s to 0.75% s/s, such concentrations being generally those which provide the desired boost in acceleration.

The admixtures of this invention can be added to cement compositions in any conventional manner familiar to those in the art. The admixture should be substantially uniformly mixed with the cement composition.

The following examples are given for illustrative purposes only. Unless otherwise indicated, all parts and proportions are by weight.

Example 1

An admixture was prepared consisting of calcium nitrate and calcium nitrite, in a 2:1 ratio, in water. The total % solids of the admixture was 42.6%.

Example 2

An admixture of the invention was prepared consisting of calcium nitrate, calcium nitrite, and glycerol, in a 2:1:1 ratio (by weight), in water. The total % solids of the admixture was 45%.

Example 3

The admixtures prepared in Examples 1 and 2 were each added individually to mortars prepared using a Type I-II portland cement, sand, and a water to cement ratio of 0.45. A blank mortar, containing no admixture,

was also prepared. Each mortar was prepared by combining 4500g of sand, 900g of H₂O, and 2000g of cement in a Hobart mixer until homogeneous. A sufficient amount of the admixture solutions of Examples 1 and 2 was added to provide an admixture solids concentration of 0.5% s/s, and 2.0% s/s, based on the weight of hydraulic cement in the admixture. Set times were measured in accordance with ASTM C403. The test was performed at 55°F.

Table 1 presents the data, which demonstrate, at different addition rates, the utility of adding a glycol component of the invention (glycerol), to improve the performance of a set-accelerating compound, in this case a mixture of calcium nitrate and calcium nitrite.

Example 4

An admixture of the invention was prepared consisting of calcium nitrate, calcium nitrite and glycerol, in a proportion of 60:16:24 (by weight), in water. The total % solids of the admixture was 45%.

Example 5

The admixture prepared in Example 4 was added to mortars prepared using three different Type I-II Portland cements ("Cements 1, 2, and 3"), sand, and a water to cement ratio of 0.45. Blank mortars, containing no admixture, were also prepared with each cement. Each mortar was prepared by combining 4500g of sand, 900g of H₂O, and 2000g of cement in a Hobart mixer until homogeneous. A sufficient amount of the admixture solution of Example 4 was added to provide an admixture solids concentration of 2.5% s/s, based on the weight of hydraulic cement in the admixture. Set times were measured in accordance with ASTM C403. The test was performed at 40°F.

Table 2 presents the results, which show the set time performance with the three cement types. The data demonstrate the cold-temperature performance of a set accelerating cement admixture of the invention.

The preceding description of the invention has been intended to illustrate rather than limit the invention. The inventors intend that various modifications or changes be made within the scope of the appended claims without departing from the spirit of the invention.

Table 1

Admixture of Example #	Initial Set Time (hr)	Change In Initial Set Time (hr)
blank	11.08	-
1 (at 0.5% s/s)	8.94	2.14
2 (at 0.5% s/s)	7.97	3.11
1 (at 2.0% s/s)	5.05	6.03
2 (at 2.0% s/s)	3.74	7.34

Table 2

Admix. of Example #	Initial Set Time (hr)			
	Cement 1	Cement 2	Cement 3	Avg.
blank	9.50	11.40	10.18	10.36
4	7.57	8.57	8.33	8.16

Claims

1. An admixture for reducing the set time of a cement composition which contains a hydraulic cement binder, the admixture comprising

- (a) a set-accelerator component; and
- (b) a C₂ to C₆ glycol component, present in an amount effective to increase the set acceleration properties of the set-accelerator component.

- 5 2. An admixture according to claim 1 wherein the amount of glycol component in the admixture is from 0.05 to 40 weight %, based on the combined weight of glycol component and accelerator component in the admixture.
- 10 3. An admixture according to claim 1 wherein the amount of glycol component in the admixture is from 2.0 to 30 weight %, based on the combined weight of glycol component and accelerator component in the admixture.
- 15 4. An admixture according to any one of claims 1 to 3 wherein the set-accelerating component is an alkali or alkaline earth metal salt of an organic or inorganic acid, or a mixture thereof.
- 20 5. An admixture according to claim 4 wherein the set-accelerating component is calcium nitrate, calcium nitrite, or a mixture thereof.
- 25 6. A cement composition comprising a hydraulic cement binder and
 - (a) a set-accelerator component; and
 - (b) a C₂ to C₆ glycol component in an amount effective to increase the set acceleration properties of the set-accelerator component.
- 30 7. A composition according to claim 6 wherein the amount of glycol component is from 0.05% s/s to 1.0% s/s, based on the amount of hydraulic cement binder in the composition.
- 35 8. A composition according to claim 6 wherein the amount of glycol component is from 0.1% s/s to 0.75% s/s, based on the weight of hydraulic cement binder in the composition.
- 40 9. A composition according to claim 6, 7 or 8 wherein the set-accelerator and/or the glycol are as defined in any one of claims 2 to 5.
- 45 10. A method for making a cement composition according to any one of claims 6 to 9 which contains a hydraulic cement binder, said method comprising adding to said cement composition
 - (a) a set-accelerator component; and
 - (b) a C₂ to C₆ glycol component, in an amount effective to increase the set acceleration properties of the set-accelerator component.
- 50 11. A method according to claim 10 wherein the set-accelerating component and glycol are as defined in any one of claims 2 to 5.
- 55 12. A corrosion-inhibiting, set-accelerating admixture for reducing the set time of a cement composition which contains a hydraulic cement binder, said admixture comprising
 - (a) a set-accelerator component comprising a mixture of alkaline earth metal nitrate and alkaline earth metal nitrite; and
 - (b) a C₂ to C₆ glycol component, present in an amount effective to increase the set acceleration properties of the set-accelerator component.
13. An admixture according to claim 12 wherein the glycol component is glycerol and the set-accelerating component is a mixture of calcium nitrate and calcium nitrite.
14. A product comprising
 - (a) a set-accelerator component comprising a mixture of alkaline earth metal nitrate and alkaline earth metal nitrite; and
 - (b) a C₂ to C₆ glycol component, present in an amount effective to increase the set acceleration properties of the set-accelerator component;
 for simultaneous, separate or sequential use in reducing the set time of a cement composition which contains a hydraulic cement binder.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

DOCUMENTS CONSIDERED TO BE RELEVANT			EP 93300546.4
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. CL.5)
X	DE - A - 3 636 659 (JSSLEDOVATELSKI CENTAR PO TEHNOLOGII KONSTRUKCII I MATERIALI "TEKOM") * Claims *	1, 2, 4, 6-14	C 04 B 24/02 C 04 B 22/08 C 04 B 40/00
X	DE - A - 2 600 563 (LUDWIG HÖRLING, FABRIK CHEMISCHER BAUSTOFFE GMBH) * Claims *	1, 4, 6, 10, 12, 14	
X	FR - A - 2 227 240 (SOCIETE FRANCAISE LANCO) * Claims; page 3, lines 33-35 *	1, 6, 10, 12, 14	
X	JP - A - 63-319 235 (ARAKI MASANORI) * Totality *	1, 6, 10, 12, 14	
X	JP - A - 58-185 458 (OSAKA CEMENT KK) * Totality *	1, 4-6, 9, 10, 12-14	TECHNICAL FIELDS SEARCHED (Int. CL.5)
X	JP - A - 55-32 800 (DENKI KAGAKU KOGYO KK) * Totality *	1, 4, 6, 10, 12, 14	C 04 B
X	SU - A - 1 648 920 (GHERSONSKII SELSKOCHOEJAST- WENIY INSTITUT IM.A.D. ZYURUPY) * Totality *	1, 4, 6, 10, 12, 14	
X	SU - A - 910 538 (WSESOJUNYI NAUTSCHNO- -JSSLEDOWATELSKII INSTITUT TRANSPORTNOGO STROITELSTWA) * Claims *	1, 4, 6, 10, 12, 14	
The present search report has been drawn up for all claims			
Place of search VIENNA		Date of completion of the search 12-03-1993	Examiner BECK
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons</p> <p>& : member of the same patent family, corresponding document</p>			



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

-2-

EP 93300546.4

DOCUMENTS CONSIDERED TO BE RELEVANT			CLASSIFICATION OF THE APPLICATION (Int. CL.5)
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	
X	SU - A - 697 455 (TOMSKII INSHENERNO-STROITELNII INSTITUT) * Totality *	1, 4, 6, 10, 12, 14	
X	WO - A - 89/08 627 (MARLEY TILE AG et al.) * Claims 1, 8 *	1-4, 6- 12, 14	
			TECHNICAL FIELDS SEARCHED (Int. CL.5)
The present search report has been drawn up for all claims			
Place of search VIENNA		Date of completion of the search 12-03-1993	Examiner BECK
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

THIS PAGE BLANK (USPTO)